



## Re-coat Existing Metacrylics<sup>®</sup> Roof: 5-Year System

### Materials Needed:

Product	Application Rate	Application Calculator
Clear Acrylic Base	1 gallons/SQ	1 x ___ SQs = ___ Gallons
Acrylic White	2 gallons/SQ	2 x ___ SQs = ___ Gallons
Acrylic Gel	As Needed	

NOTE: 1 SQ = 100 sq. ft.

Always consult your Metacrylics<sup>®</sup> rep or contact Metacrylics for full system specifications.

### General Application Guidelines

1. Thoroughly pressure wash roof.
2. Apply Metacrylics<sup>®</sup> Clear Acrylic Base @ 1 gallons/SQ to the entire roof. Allow 4-12 hours to cure.
3. Apply Metacrylics<sup>®</sup> Acrylic White @ 2 gallons/SQ to the entire roof. Allow 24-48 hours to cure.



**Metacrylics**<sup>®</sup>  
energy efficient coatings

## Re-coat Existing Metacrylics<sup>®</sup> Roof: 10-Year System

### Materials Needed:

Product	Application Rate	Application Calculator
Clear Acrylic Base	1 gallons/SQ	1 x ___ SQs = ___ Gallons
Acrylic White	3 gallons/SQ	3 x ___ SQs = ___ Gallons
Acrylic Gel	As Needed	

NOTE: 1 SQ = 100 sq. ft.

Always consult your Metacrylics<sup>®</sup> rep or contact Metacrylics for full system specifications.

### General Application Guidelines

1. Thoroughly pressure wash roof.
2. Apply Metacrylics<sup>®</sup> Clear Acrylic Base @ 1 gallons/SQ to the entire roof. Allow 4-12 hours to cure.
3. Apply Metacrylics<sup>®</sup> Acrylic White @ 3 gallons/SQ to the entire roof in two applications at the rate of 1.5 gallons/SQ. Allow 24-48 hours to cure.



365 Obata Court, Gilroy, CA 95020  
PHONE: (408) 280-7733 | FAX: (408) 280-6329  
metacrylics.com



## Re-coat Existing Metacrylics<sup>®</sup> Roof: 15-Year System

### Materials Needed:

Product	Application Rate	Application Calculator
Clear Acrylic Base	1 gallons/SQ	1 x ___ SQs = ___ Gallons
Acrylic White	4 gallons/SQ	4 x ___ SQs = ___ Gallons
Acrylic Gel		As Needed
Stitchbond Fabric		As Needed

NOTE: 1 SQ = 100 sq. ft.

Always consult your Metacrylics<sup>®</sup> rep or contact Metacrylics for full system specifications.

### General Application Guidelines

1. Thoroughly pressure wash roof.
2. Apply Metacrylics<sup>®</sup> Clear Acrylic Base @ 1 gallons/SQ to the entire roof. Allow 4-12 hours to cure.
3. 3-course penetration detail (see Metacrylics<sup>®</sup> Penetration Detail Instructions).
4. Apply Metacrylics<sup>®</sup> Acrylic White @ 4 gallons/SQ to the entire roof in two applications at the rate of 2 gallons/SQ. Allow 24-48 hours to cure between applications.



## Re-coat Existing Metacrylics<sup>®</sup> Roof: 20-Year System

### Materials Needed:

Product	Application Rate	Application Calculator
Clear Acrylic Base	1 gallons/SQ	1 x ___ SQs = ___ Gallons
Acrylic White	5 gallons/SQ	5 x ___ SQs = ___ Gallons
Acrylic Gel		As Needed
Stitchbond Fabric		As Needed

NOTE: 1 SQ = 100 sq. ft.

Always consult your Metacrylics<sup>®</sup> rep or contact Metacrylics for full system specifications.

### General Application Guidelines

1. Thoroughly pressure wash roof.
2. Apply Metacrylics<sup>®</sup> Clear Acrylic Base @ 1 gallons/SQ to the entire roof. Allow 4-12 hours to cure.
3. 3-course penetration detail (see Metacrylics<sup>®</sup> Penetration Detail Instructions).
4. Apply Metacrylics<sup>®</sup> Acrylic White @ 5 gallons/SQ to the entire roof. In three applications at the rate of 1.66 gallons/SQ. Allow 24-48 hours to cure between coats.



## Re-coat Existing Metacrylics<sup>®</sup> Roof: 30-Year System

### Materials Needed:

Product	Application Rate	Application Calculator
Clear Acrylic Base	1 gallons/SQ	1 x ___ SQs = ___ Gallons
Acrylic White	7 gallons/SQ	7 x ___ SQs = ___ Gallons
Acrylic Gel		As Needed
Stitchbond Fabric		As Needed

NOTE: 1 SQ = 100 sq. ft.

Always consult your Metacrylics<sup>®</sup> rep or contact Metacrylics for full system specifications.

### General Application Guidelines

1. Thoroughly pressure wash roof.
2. Apply Metacrylics<sup>®</sup> Clear Acrylic Base @ 1 gallons/SQ to the entire roof. Allow 4-12 hours to cure.
3. 3-course penetration detail (see Metacrylics<sup>®</sup> Penetration Detail Instructions).
4. Apply Metacrylics<sup>®</sup> Acrylic White @ 7 gallons/SQ to the entire roof. In four applications at the rate of 1.75 gallons/SQ. Allow 24-48 hours to cure between coats.