

PERMEABILITY: 0.016 Perms ASTM D1653 (81 mils dry film thickness) (Water Vapor Transmission)

WIND UPLIFT: 105 PSF Section 6 of ANSI A58.1, Min. Design Loads for Building and Other Structures

FIRE RESISTANCE: Class A ASTM E-108 UL Standard 790 (1,400° F Flame & Wind Velocity 1,050 ft./minute)

CHEMICAL RESISTANCE

Gasoline - some softening and spotting
1% Sodium hydroxide alkali (no effect)
1% Hydrochloric acid (no effect)
Sodium chloride/salt (no effect)
Petroleum ether or naphtha (no effect)

Lubricating Oil - some spotting
Diesel (no effect)
Stoklard solvent (no effect)
Boric acid (no effect)

SAYBOLT FUROL: At 122° F is 265 Sec. AASHTOT 59

DEMULSIBILITY: No reaction AASHTOT 59

TOXICITY: Not for use with potable water

PARTICLE CHARGE: Negative

WEIGHT: 12.1 lbs./gallon

VOC (VOLATILE ORGANIC CONTENT): 27.5 grams/liter

SOLIDS CONTENT (by weight): 68.4%

APPLICATION

SURFACE PREPARATION Surfaces should be clean, dry, free of dust, dirt and oily residues. Remove loose rust from metal, and wipe new galvanized metal with acidic acid solution prior to application. Metacrylics Primer is recommended for all surfaces. New concrete must be fully cured. New glazed asphalt and torch down single-ply assemblies should wait 6 months or more before application.

SPRAY APPLICATION & COVERAGE RATES Apply 2 coats of ACRYLIC WHITE @ 1.5 gallons/100 sq. ft. per application (total 3 gallons/100 sq.ft.) using a .035 - .039 spray tip. (MORE COATS OR MORE PRODUCT PER APPLICATION COULD BE REQUIRED FOR LONGER TERM COATING SYSTEMS) Allow a full 24 hours between applications or longer if necessary based on local weather conditions in order to prevent blistering. *Hints: Don't spray on windy days! Use barricades around the job. Visqueen all skylights not to be coated. Be sure to have 1/2 a barrel of water to flush the pump and hose when finished. Be sure to have extra tips and TSL Throat Seal Liquid.*

ROLLER APPLICATION AND COVERAGE RATES

Apply 2 coats @ 1.5 gals /100 sq. ft. per application (total of 3 gals/100 sq. ft.) (More coats and more product per application are required for longer lasting coating systems). Allow a full 24 hours or longer between applications if necessary based on local weather conditions in order to prevent blistering.

NON-SKID APPLICATION Sand may be gently broadcasted over the wet acrylic WHITE, or mix 1/2 gallon of #30 mesh sand, rubber granules, etc. with 2.5 gallons of ACRYLIC WHITE using a stick or electric drill with mixing paddle, add more or less sand to desired consistency. Apply with a texture roller or texture gun.

HINTS Allow a full 24 hours or longer between coats if necessary based on local weather conditions in order to prevent blistering. Cold temperatures slow down the drying times. Start early, stop early! Application in hot temperatures should be avoided or blistering of the coating may occur. If any Acrylic WHITE is left over, apply additional coats until all product is used. Three gallons per 100 sq. ft. is necessary to prevent delamination in ponding areas and to maintain superior performance under UV and freezing conditions.

CLEAN-UP Clean tools and equipment with water. Cured material may be removed with amylacetate, hand cleaner, or lacquer thinner. Do not use these materials (except hand cleaner) on bare skin.

THINNING Thin with water if necessary.

STORAGE Store in areas where temperature remains above 40... F. Prior to use agitate for 2-3 minutes by hand or machine. Reseal opened containers. If contents skin, remove skin, agitate, use immediately. If the product has been stored for a months (or years), remove any surface skin that may have developed, stir, and immediately use.

IMPORTANT APPLICATION INFORMATION

DO NOT APPLY if rain or freezing weather is imminent within 24 hours following application, or during fog or drizzle. This product is water-based and could wash off if not fully cured.

KEEP AWAY FROM CHILDREN.

DO NOT APPLY when temperatures are consistently below 40° F. The Acrylic White dries slowly when temperatures are below 55° F. Areas shaded from sunlight dry very slowly. Seventy-two hours or more may be required for proper curing.

DO NOT THIN or add solvents.

PROTECT MATERIALS from freezing and extreme heat.

CAUTION! Wet acrylic is extremely slippery when stepped on. Use a safety rope around you on sloped surfaces.